

GOLD GREASE

DESCRIPTIONS:

This product is a tough, durable gold colored non-soap bentone base, non-melt grease, fortified with extreme pressure additives that provide a timken load capacity of 65.

This is one of very few grease compounds that is designed to absorb shock loads and impact pressures of 65 timken load capabilities; yet remain extremely stable under a wide variety of conditions including heat, moisture, acid and alkalies.

COMPOSITION & CHARACTERISTICS:

This product is manufactured from carefully selected base stocks to meet the most critical industrial and commercial requirements.

The polarity of this excellent grease provides greater metal adhesion and protection from corrosive atmospheres including strong acids and alkalies.

The product will not melt and run even at high operating temperatures.

The unique combination of high viscosity index paraffinic base stocks, modifiers and improvers, coupled with an inorganic gelling agent, enables the grease to be pumped equally well in low or high temperatures.

USES:

As an all-purpose grease. This product has an extremely wide range of applications. Here are a few:

Ball & Roller Bearings	Disc Brakes
Sleeve Bearings	Fifth Wheels
Wheel Bearings	King Pins

This product not only lubricates better, but because of its tenacious film strength, will last longer and require less replacement and less frequent lubrication.



P.O. BOX 430
Conway, AR 72033

TO REORDER CALL:
1-800-282-2133 OR
(501)329-6965

GOLD GREASE

**PREMIUM NON-MELTING
ALL-PURPOSE GREASE**

RUST & CORROSION INHIBITORS

WITHSTANDS EXTREME PRESSURE

SHOCK AND IMPACT RESISTANT

TIMKEN LOAD OF 65

ALL WEATHER PERFORMANCE

CAUTION:

KEEP OUT OF REACH OF CHILDREN. Do not take internally. See side panel for additional precautionary information.

NET CONTENTS 45 LBS (20.4 KGS)

TYPICAL APPLICATIONS:

NLGI Number	2
ASTM Penetration (60 strokes)	265-295
ASTM-D 1263-61 Wheel Bearing Test	
Grease Leakage	0.3
Condition	Excellent
Ford Wheel Bearing Test	Pass
ASTM Dropping Point	Non-melt
Timken E.P. Test Load	65
Water Resistance	Excellent
Acid Resistance	Excellent
Base Oil	
Viscosity SUS @ 100°F	600.0
Viscosity CTS @ 100°F	129.2
Viscosity SUS @ 210°F	68.7
Viscosity CTS @ 210°F	12.7
Viscosity Index	96

CAUTION:

Do not ingest. If this should occur, drink large volumes of water and seek medical attention. Avoid storage of product in freezing temperatures. Keep container sealed when not in use. Rinse empty container before discarding in an authorized landfill site. **KEEP OUT OF REACH OF CHILDREN.**

1036683 05/94